

ALTUGLAS® CN IRIDESCENT

The Altuglas® CN Iridescent is an opal product with 'colour' appearance in reflection observed under different angles.

The translucent range has an effect from medium opal towards gold, green, violet, purple or red.


The iridescent effect is the result of specific character and orientation of components involved. Therefore effect and intensity of it will vary depending on viewing angle.

Because of the 'lively' behaviour of its composition some slight variation in appearance could occur. This variation could be within the sheet or from sheet to sheet.

It can be easily cut, drilled and glued. For thermoforming line bending and drape moulding is possible, stretching is not recommended. The Altuglas® CN Iridescent can also be produced in other grades, like: satin or Essential.

The Iridescent sheets are delivered with top face downwards!

MAIN PROPERTIES

PMMA (Polymethylmethacrylate)	
Light	
Transparent	
UV resistant - No Yellowing	
Thermoformable	
Easy machining	



MAIN APPLICATIONS

- furniture
- shop fitting
- POP - POS
- Decoration
- Eye catching objects

PACKAGING

- our standard film offers a strong adhesion thanks to an additional adhesive layer. On demand a dedicated thermoformable film can be proposed
- our product is store on wood pallets with a PP sheet at the bottom and a cardboard at the top
- the total weight of the pallet + sheets is less than one ton

STORAGE

The following rules has to be applied

- store the product in a dry place, indoors
- place a polyethylene cover over the stack when a sheet is removed, to reduce moisture absorption.
- only use original delivery pallets
- stack pallets of the same size and design to prevent waving
- place pallets on even surfaces (floor or shelf)
- the durability of the protective film is limited (sensitive to UV, temperature, humidity and chemicals)

ALTUGLAS® CN IRIDESCENT

CERTIFICATES

- Altuglas International guarantees that its Altuglas® CN clear product of any thickness up to 25 mm, retain virtually all their characteristics after 10 years exposure to weather. This guarantee covers light transmission, rigidity and tensile strength. Our ten year guaranty is available on demand.
- our sheets rely to the norm ISO 7823-1 : 2003 regarding types, dimensions and characteristics
- our management system fulfils the requirements of the ISO 9001 : 2008

TECHNICAL SPECIFICATIONS

	Measurement Method	Unit	Value
General Characteristics			
Density	ISO 1183	g/cm ³	1.19
Water absorption (24h)	ISO 62	%	0.3
Water absorption (8 days)	ISO 62	%	0.5
Thickness tolerance		± (0,4 mm + 0,1 x thickness)	
Mechanical properties			
Modulus of elasticity (23°C)	ISO 527-2	MPa	3300
Tensile strength (23°C)	ISO 527	MPa	76
Charpy impact strength (un-notched)	ISO 179/2D	KJ/m ²	12
Surface hardness (Rockwell scale M)	IS 2039	-	100
Thermal properties			
Vicat softening point (B50)	ISO 306	°C	115
Coefficient of linear expansion	ISO 11359	mm/m/°C	0.065
Maximum continuous service temperature	-	°C	85
Maximum heating temperature	-	°C	200
Linear shrinkage after heating		%	< 2
Forming temperature	-	°C	165-190
Optical properties			
Light transmittance (3 mm)	ISO 13468	Depending on reference	
Flammability			
Self-ignition temperature	-	°C	~ 450
Melt behaviour when burning	-	-	Non drip
Glow wire resistance	EN 60695-2-11	°C	750
Euroclass classification	EN 13501	-	E
UL	UL 94	-	HB

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <http://www.arkema.com/en/products/product-safety/disclaimer/index.html>

See MSDS for Health & Safety Considerations